



FEEL THE SW
DIFFERENCE®

COMFORT AND DEXTERITY FOR EVERYDAY HAND PROTECTION.



TF-95RB

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES*

VALUE AND PERFORMANCE HAND PROTECTION FOR LAB, LIFE SCIENCE AND INDUSTRIAL ENVIRONMENTS

- EcoTek® Sustainable Technology*
- Silicone-free for critical environments
- Exceeds 1.5 AQL laboratory standards

TF

TF-95RB

WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR
 5.0g (large size)	 9.5"	 4.7 mil 3.1 mil	EcoTek®	ROYAL BLUE


ECOTEK



Finger textured
surface for wet
and dry grip

The right weight
for resiliency and
dexterity

Tear-resistant
beaded cuff for
easy donning



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347
Trademarks and registered trademarks are the property of SW and its affiliates.
©2025 SW. All rights reserved.



TECHNICAL DATA



TF-95RB

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE EXAMINATION GLOVES*

POLYCARBIN

THIS GLOVE IS RECYCLABLE THROUGH
POLYCARBIN'S LAB RECYCLING PROGRAM.

PRODUCT DESCRIPTION

SPECIFICATIONS

PRODUCT	TrueForm®
GRADE	Powder-Free Exam
MATERIAL	Nitrile
THICKNESS FINGER	4.7mil 0.12mm
PALM	3.1mi 0.08mm
COLOR	Royal Blue
SURFACE	Finger Textured
LENGTH	9.5" 242mm
WEIGHT	5.0g
FIT TYPE	Ambidextrous
CUFF TYPE	Beaded
WATERTIGHT AQL	1.5
ORIGIN COUNTRY	Malaysia

PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
TENSILE STRENGTH:	14 MPA	14 MPA
ELONGATION:	500%	400%

INTEGRATED TECHNOLOGIES

ECOTEK Sustainable Technology: Product has been tested per ASTM D5526*



* Specifications based on size Large glove

STANDARDS & CERTIFICATIONS

EN ISO 21420:2020
EN 455-2000-2015
ASTM D6319-19
ASTM D6978-05 (2019)
ASTM F1671-13
ASTM F739-12
Reach EU 1907/2006

EU 2016/425
ANSI/ISEA 105-2016
CAT III Complex Design
FDA 21 CFR 177.2600



Please visit swssglobal.com/symbols for information on standards used on this document.

ORDERING

ITEM NO.	SIZE	PALM WIDTH	PACKAGING
N301341	XS 5½ – 6	3.0" 75mm	100 gloves per box 10 boxes per case
N301342	S 6½ – 7	3.3" 85mm	100 gloves per box 10 boxes per case
N301343	M 7½ – 8	3.7" 95mm	100 gloves per box 10 boxes per case
N301344	L 8½ – 9	4.1" 105mm	100 gloves per box 10 boxes per case
N301345	XL 9½ – 10	4.5" 115mm	100 gloves per box 10 boxes per case
N301346	2XL 10½ – 11	4.9" 125mm	100 gloves per box 10 boxes per case

TECHNOLOGY PATENTS

US 12,201,172 B2

Multiple U.S. and other patents pending.

APPLICATIONS

For Medical Use
Chemical Handling
Dental
Veterinary

Keep out of sunlight. Store in a cool, dry place.
Keep away from sources of ozone or ignition.



R_N30134X0825



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347
Trademarks and registered trademarks are the property of SW and its affiliates.
©2025 SW. All rights reserved.



*EcoTek gloves tested to ASTM D5526-12 Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions. Results are 92.6% biodegradation in 60% solids landfill at 945 days. Future results cannot be predicted/extrapolated. If you need more information on the test reports, send email to cs@swssglobal.com.